

## Style 332-1-AL TECHNICAL DATA

Base Fabric		Tolerance	Test Methods
Yarn			DIN 53830-3
Warp	EC9 136 tex	± 5%	
Weft	EC9 136 tex	± 5%	
Thread Count			DIN EN 1049-2
Warp	18,0 1/cm	± 5%	
Weft	13,0 1/cm	± 5%	
Weight	430 g/m <sup>2</sup>	± 5%	DIN EN 12127
Weave	Cross Twill		ISO 9354
Temperature Resistance	550°C		

Coated Fabric		Tolerance	Test Methods
Coating:	laminated with an aluminium-foil of ~ 12 µm thickness with high temperature adhesive on one side		
Weight	480 g/m <sup>2</sup>	± 10%	DIN EN 12127
Thickness	0,43 mm	± 10%	DIN EN ISO 5084
Tensile Strength			DIN EN ISO 13934-1
Warp	> 6.000 N/5cm		
Weft	> 4.500 N/5cm		
Temperature Resistance:	Adhesive: Apr. 180 °C		

