

Style 2025 9480 HT TECHNICAL DATA

Base Fabric		Tolerance	Test Methods
Yarn			DIN 53830-3
Warp	EC9 134 tex	± 5%	
Weft	EC9 134 tex	± 5%	
Thread Count			DIN EN 1049-2
Warp	8,0 1/cm	± 5%	
Weft	6,0 1/cm	± 5%	
Weight	605 g/m ²	± 5%	DIN EN 12127
Weave	Plain		ISO 9354
Temperature Resistance	550°C		

Coated Fabric		Tolerance	Test Methods
Coating:	side 1: aluminium foil laminated with high temperature adhesive		
	side 2: uncoated E-glass fabric		
Weight	663 g/m ²	± 10%	DIN EN 12127
Thickness	0,66 mm	± 10%	DIN EN ISO 5084
Tensile Strength			DIN EN ISO 13934-1
Warp	> 2.100 N/5cm		
Weft	> 2.100 N/5cm		
Temperature Resistance:	270 °C after 24 h		
	250 °C after 500 h		

