

Style 1000-2-HT white TECHNICAL DATA

| Base Fabric | | Tolerance | Test Methods |
|------------------------|------------------------|---------------------|---------------|
| Yarn | | | DIN 53830-3 |
| Warp | ET9 | 860 tex $\pm 5\%$ | |
| Weft | ET9 | 1,400 tex $\pm 5\%$ | |
| Thread Count | | | DIN EN 1049-2 |
| Warp | 6.0 1/cm | $\pm 5\%$ | |
| Weft | 4.0 1/cm | $\pm 5\%$ | |
| Weight | 1.020 g/m ² | $\pm 5\%$ | DIN EN 12127 |
| Weave | Plain | | ISO 9354 |
| Temperature Resistance | 550°C | | |

| Coated Fabric | | Tolerance | Test Methods |
|-------------------------|---|------------|--------------------|
| Coating: | coated with an inorganic high temperature treatment (available in different colours) | | |
| Weight | 1.05 g/m ² | $\pm 10\%$ | DIN EN 12127 |
| Thickness | 1,50 mm | $\pm 10\%$ | DIN EN ISO 5084 |
| Tensile Strength | | | DIN EN ISO 13934-1 |
| Warp | > 2.300 N/5cm | | |
| Weft | > 2.200 N/5cm | | |
| Temperature Resistance: | 700 °C | | |

