

Style 3259-2-SBK - TECHNICAL DATA

Base Fabric		Tolerance	Test Methods
Yarn			DIN 53830-3
Warp	EC9 134 tex	± 5%	
Weft	EC9 134 tex	± 5%	
Thread Count			DIN EN 1049-2
Warp	19,0 1/cm	± 5%	
Weft	13,0 1/cm	± 5%	
Weight	430 g/m ²	± 10%	DIN EN 12127
Weave	Satin	ISO 9354	
Temperature Resistance	550°C		

Coated Fabric		Tolerance	Test Methods
Coating:	coated with high temperature flame retardant black silicone rubber on both side		
Weight	595 g/m ²	± 10%	DIN EN 12127
Thickness	0,46 mm	± 10%	DIN EN ISO 5084
Tensile Strength			DIN EN ISO 13934-1
Warp	> 2.900 N/5cm		
Weft	> 2.100 N/5cm		
Temperature Resistance	-55 - 260°C		

