

Style Sil 600 TECHNICAL DATA

Silica Content	~ 95 %		
Base Fabric		Tolerance	Test Methods
Yarn			DIN 53830-3
Warp	68 × 2 tex	± 5%	
Weft	68 × 2 tex	± 5%	
Thread Count			DIN EN 1049-2
Warp	19,0 1/cm	± 5%	
Weft	13,0 1/cm	± 5%	
Weight	600 g/m ²	± 5%	DIN EN 12127
Weave	Satin		ISO 9354
Temperature Resistance	1000°C		

Coated Fabric	Tolerance	Test Methods	
Coating: coated with high-temperature-resistant, light-brown vermiculite			
Weight	650 g/m ²	± 10%	DIN EN 12127
Thickness	0,60 mm	± 10%	DIN EN ISO 5084
Tensile Strength			DIN EN ISO 13934-1
Warp	> 1.100 N/25cm		
Weft	> 800 N/25cm		
Temperature Resistance:	1000 °C		

