

Style FCF 1650 metallic TECHNICAL DATA

Base Fabric		Tolerance	Test Methods
Yarn			DIN 53830-3
Warp	EC9 134 tex	± 5%	
Weft	EC9 134 tex	± 5%	
Thread Count			DIN EN 1049-2
Warp	19,0 1/cm	± 5%	
Weft	13,0 1/cm	± 5%	
Weight	430 g/m ²	± 5%	DIN EN 12127
Weave	Satin		ISO 9354
Temperature Resistance	550°C		

Coated Fabric		Tolerance	Test Methods
Coating:	coated with high temperature, flame retardant, metallic-shiny PTFE on one side		
Weight	561 g/m ²	± 10%	DIN EN 12127
Thickness	0,38 mm	± 10%	DIN EN ISO 5084
Tensile Strength			DIN EN ISO 13934-1
Warp	> 3.500 N/5cm		
Weft	> 2.600 N/5cm		
Temperature Resistance:	101°C to 315 °C		

