

## Style 8566-2-SS TECHNICAL DATA

<b>Base Fabric</b>		<b>Tolerance</b>	<b>Test Methods</b>
<b>Yarn</b>			DIN 53830-3
Warp	EC9 204 tex	± 5%	
Weft	EC9 204 tex	± 5%	
<b>Thread Count</b>			DIN EN 1049-2
Warp	16,0 1/cm	± 5%	
Weft	15,0 1/cm	± 5%	
<b>Weight</b>	660 g/m <sup>2</sup>	± 5%	DIN EN 12127
<b>Weave</b>	Satin		ISO 9354
<b>Temperature Resistance</b>	550°C		

<b>Coated Fabric</b>	<b>Tolerance</b>	<b>Test Methods</b>
<b>Coating:</b>	coated with high temperature flame retardant silver-grey silicone rubber on both sides	
<b>Weight</b>	900 g/m <sup>2</sup>	± 10%      DIN EN 12127
<b>Thickness</b>	0,66 mm	± 10%      DIN EN ISO 5084
<b>Tensile Strength</b>		DIN EN ISO 13934-1
Warp	> 4.600 N/5cm	
Weft	> 4.400 N/5cm	
<b>Temperature Resistance:</b>	250°C	

