

Style 332-2-PU TECHNICAL DATA

Base Fabric		Tolerance	Test Methods
Yarn			DIN 53830-3
Warp	EC9 136 tex	± 5%	
Weft	EC9 136 tex	± 5%	
Thread Count			DIN EN 1049-2
Warp	18,0 1/cm	± 5%	
Weft	13,0 1/cm	± 5%	
Weight	420 g/m ²	± 5%	DIN EN 12127
Weave	Cross Twill		ISO 9354
Temperature Resistance 550°C			

Coated Fabric		Tolerance	Test Methods
Coating:	coated with silver-grey (with aluminium pigments) flame retardant PU on both sides to increase the fray-proofness and antislip-properties of the material		
Weight	460 g/m ²	± 10%	DIN EN 12127
Thickness	0,45 mm	± 10%	DIN EN ISO 5084
Tensile Strength			DIN EN ISO 13934-1
Warp	> 4.900 N/5cm		
Weft	> 4.000 N/5cm		
Temperature Resistance: 180°C			

