

Style FCF 1650 grey TECHNICAL DATA

Base Fabric	Tolerance	Test Methods
Yarn		DIN 53830-3
Warp	EC9 134 tex ± 5%	
Weft	EC9 134 tex ± 5%	
Thread Count		DIN EN 1049-2
Warp	19,0 1/cm ± 5%	
Weft	13,0 1/cm ± 5%	
Weight	430 g/m ² ± 5%	DIN EN 12127
Weave	Satin	ISO 9354
Temperature Resistance	550°C	

Coated Fabric	Tolerance	Test Methods
Coating: coated with high temperature flame retardant, PTFE on one side. Excellent resistance against various chemicals / weather and UV / high temperature / high abrasion resistance		
Meets the requirements of class A2 – s1, d0 for fire behaviour according to EN 13501-1		
Weight	561 g/m ² ± 10%	DIN EN 12127
Thickness	0,38 mm ± 10%	DIN EN ISO 5084
Tensile Strength		DIN EN ISO 13934-1
Warp	> 3.500 N/5cm	
Weft	> 2.600 N/5cm	
Temperature Resistance:	- 110°C to 315 °C	

