

Style 950-2-HT TECHNICAL DATA

Base Fabric		Tolerance	Test Methods
Yarn			DIN 53830-3
Warp	ET9	560 tex $\pm 5\%$	
Weft	ET9	560 tex $\pm 5\%$	
Thread Count			DIN EN 1049-2
Warp	10,0 1/cm	$\pm 5\%$	
Weft	6,0 1/cm	$\pm 5\%$	
Weight	950 g/m ²	$\pm 5\%$	DIN EN 12127
Weave	Cross Twill		ISO 9354
Temperature Resistance	550°C		

Coated Fabric		Tolerance	Test Methods
Coating:	coated with an inorganic high temperature treatment, color grey – flame retardant / increased temperature resistance behaviour / increased abrasion resistance		
Weight	1.000 g/m ²	$\pm 10\%$	DIN EN 12127
Thickness	1,25 mm	$\pm 10\%$	DIN EN ISO 5084
Tensile Strength			DIN EN ISO 13934-1
Warp	> 3.300 N/5cm		
Weft	> 2.200 N/5cm		
Temperature Resistance:	700 °C		

