

Style 3101-2SS TECHNICAL DATA

Base Fabric		Tolerance	Test Methods
Yarn			DIN 53830-3
Warp	EC9 136 tex	± 5%	
Weft	EC9 136 tex	± 5%	
Thread Count			DIN EN 1049-2
Warp	18,0 1/cm	± 5%	
Weft	12,0 1/cm	± 5%	
Weight	420 g/m ²	± 5%	DIN EN 12127
Weave	Cross Twill		ISO 9354
Temperature Resistance	550°C		

Coated Fabric	Tolerance	Test Methods
Coating:	coated with high temperature flame retardant silver-grey silicone rubber on one side	
Weight	540 g/m ²	± 10% DIN EN 12127
Thickness	0,36 mm	± 10% DIN EN ISO 5084
Tensile Strength		DIN EN ISO 13934-1
Warp	> 4.500 N/5cm	
Weft	> 2.500 N/5cm	
Temperature Resistance	-55 - 250°C c	

