

Style 8459-2-SS TECHNICAL DATA

Base Fabric		Tolerance	Test Methods
Yarn			DIN 53830-3
Warp	EC9 136 1×2 tex	± 5%	
Weft	EC9 136 1×2 tex	± 5%	
Thread Count			DIN EN 1049-2
Warp	17,0 1/cm	± 5%	
Weft	14,0 1/cm	± 5%	
Weight	881 g/m ²	± 5%	DIN EN 12127
Weave	Satin		ISO 9354
Temperature Resistance 550°C			

Coated Fabric	Tolerance	Test Methods
Coating:	coated with high temperature flame retardant light silver-grey silicone rubber on both sides	
Weight	1,156 g/m ²	± 10% DIN EN 12127
Thickness	0,94 mm	± 10% DIN EN ISO 5084
Tensile Strength		DIN EN ISO 13934-1
Warp	> 2.400 N/5cm	
Weft	> 2.100 N/5cm	
Temperature Resistance: 250°C		

